

PART 1 - GENERAL

- 1.01 Asphalt cement pavement surfaces for roadways, drives, parking areas, and bike paths.
- 1.02 Portland Cement concrete for sidewalks, plazas, gutters, and curbs.
- 1.03 Review design of curbs and gutters to reduce their size, profile, and extents in order to reduce damage during snow removal.

PART 2 - PRODUCTS

- 2.01 Ceramic or quarry tile not acceptable for exterior walkway use.
- 2.02 Concrete paving: Minimum 4,000 psi compressive strength with minimum 60ksi strength #3 bar at 12 inch on center both ways or WWF4x4 W2.1 x 2.1, 4 to 7 percent entrained air, and fiber mesh to control cracking. Stiff broom finish. Refer to Division 03 for additional concrete requirements.
- 2.03 2 inch minimum thickness of asphalt cement pavement meeting DOT specifications

END OF SECTION